

SPECIFICATION SHEET

	VISIBLE LIGHT			SOLAR ENERGY									
Product	VLT	Reflectivity Exterior	Reflectivity Interior	Energy Trans.	Energy Reflected	Energy Absorbed	UV Rejection	Heat Rejection TSER	Shading Coefficient	SHGC	U Factor	Emmissivity	Glare Reduction
ARCHITECTURAL													
Silver 20 DA	20	57	56	13	54	34	99	78	0.25	0.23	0.91	0.91	78
Silver 30 DA	31	42	41	22	43	35	99	67	0.37	0.31	0.92	0.92	67
Silver 45 DA	45	27	26	35	29	36	99	56	0.51	0.44	0.94	0.94	52
Bronze 20 DA	22	29	32	14	40	46	99	71	0.32	0.28	0.92	0.92	76
Bronze 35 DA	35	18	23	25	30	45	99	63	0.43	0.37	0.92	0.92	61
One-Way DA	8	57	15	9	54	37	99	81	0.23	0.19	0.96	0.96	92
Evening View 15 DA	15	49	22	14	48	39	99	76	0.29	0.24	0.96	0.96	83
Evening View 25 DA	26	27	13	29	28	44	99	61	0.47	0.39	0.99	0.99	69
Evening View 35 DA	37	13	8	41	15	44	99	44	0.63	0.56	1.02	1.02	59
Evening View 45 DA	46	8	8	50	10	40	99	37	0.73	0.63	1.05	1.05	50
Daylight 60 DA	57	8	9	53	9	38	99	36	0.76	0.67	1.07	1.07	37
Crystal Clear 70	69	21	20	49	32	19	99	46	0.62	0.54	0.96	0.96	25
Exterior Silver 20	18	59	56	15	59	26	99	78	0.26	0.22	1.02	1.02	81
SAFETY & SECURITY													
Safety Clear 4Mil	90	9	8	83	6	11	99	13	0.98	0.84	1.12	1.12	1
Safety Clear 7Mil	90	9	8	81	7	12	99	15	0.98	0.83	1.12	1.12	1
Security 8Mil	88	9	8	80	7	13	99	17	0.95	0.83	1.07	1.07	3
Security 12Mil	87	9	9	76	7	18	99	19	0.92	0.81	1.02	1.02	4
Security 15Mil	86	10	10	77	9	14	99	20	0.93	0.81	1.07	1.07	4
Security 8Mil Silver 20	18	58	58	13	53	34	99	78	0.25	0.22	0.91	0.91	80
Security 8Mil Neutral 35	36	16	23	30	19	51	99	54	0.52	0.45	0.98	0.98	60
Anti-Graffiti 4Mil	90	9	9	83	6	11	99	13	0.98	0.84	1.12	1.12	1
Anti-Graffiti 6Mil	90	9	8	81	7	12	99	15	0.98	0.83	1.12	1.12	1

* The performance data above was tested according to ASTM & AIMCOL standards. All values represented are as applied on 1/8" (3mm) glass.